

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-341103

(43)Date of publication of application : 24.12.1993

(51)Int.Cl.

G02B 1/10

(21)Application number : 04-153447

(71)Applicant : TORAY IND INC

(22)Date of filing : 12.06.1992

(72)Inventor : KURASAKI SHOICHI  
TANIGUCHI TAKASHI  
HOSONO HIROSHI

## (54) ARTICLE HAVING REFLECTION PREVENTING PROPERTY

## (57)Abstract:

PURPOSE: To improve charge preventing property, reflection preventing property, wear resistance and transparency by providing a transparent conductive coat and a specified coat on a part of a transparent base in this order.

CONSTITUTION: On a part of a transparent base, a transparent conductive coat is formed. Further, a transparent coat obtained from a liquefied composite containing 20wt% or more of a compound selected from organic polysiloxane compounds and their hydrolyzates, which is represented by the formula I or II, is formed thereon. In the formula I, R<sup>1</sup>, R<sup>2</sup> represent substituents selected from alkyl group, alkenyl group and halogen group, R represents a substituent selected from C1-C8 alkyl group, alkoxyalkyl group, and acyl group. (a), (b) represent 0 or 1. In the formula II, R<sup>3</sup> represents a C1-C20 fluorine-contained alkyl group, Q represents a divalent organic group, X represents a C1-C5 alkyl group, Y represents a substituent selected from halogen and alkoxy group, and C is 0 or 1.



## LEGAL STATUS

[Date of request for examination] 11.05.1999

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3240685

[Date of registration] 19.10.2001

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's]